

PRIMER



UNIVERSAL PRIMER FOR ACRYLIC ADHESIVE TAPES

LOW PROFILE

The solvent-free acrylic dispersion mix ensures its transparency.

PRACTICAL

Ready to use, compensates for irregularities on rough surfaces and guarantees fast drying.



TECHNICAL DATA

Properties	value	USC units
Composition	acrylic dispersion without solvents	-
Density	approx. 1,02 g/ml	8.51 lb/gal
Viscosity	approx. 1700 mPa-s	-
Time required for drying 20 °C/50 %RH	approx. 15 min	-
Application temperature (cartridge, ambient and support)	+5/+30 °C	+41/+86 °F
Temperature resistance after drying	-30/+80 °C	-22/+176 °F
Emicode (GEV test procedure)	EC1 plus	-
French VOC classification	A+	-
Transport temperature	-26/+35 °C	-14.8/+95 °F
Storage temperature ⁽¹⁾	+15/+25 °C	+59/+77 °F

⁽¹⁾Store the product in a dry place and check the date of manufacture on the cartridge.

Waste classification (2014/955/EU): 08 04 10.

EUH208 Contains CAS 55965-84-9 (3:1), CAS 2634-33-5. May produce allergic reactions; EUH210 Safety data sheet available on request.

CODES AND DIMENSIONS

CODE	content	yield	content	yield	
	[ml]	[mL/m ²]	[US fl oz]	[US fl oz/ft ²]	
PRIMER	1000	100/200	33.81	0.32/0.63	6



PACKAGING

The new packaging allows immediate installation without the need for additional tools.

RE-CLOSABLE

The cap perfectly seals the packaging, ensuring a longer product life and preventing accidental leaks during transport.