


BYTUM 1500

BITUMINOUS UNDERLAY CONTROL LAYER

CE
EN 13859-1
EN 13707

COMPOSITION

- ① top layer: non-woven PP fabric
- ② compound: bituminous mix
- ③ reinforcing layer: PL fabric
- ④ compound: bituminous mix
- ⑤ bottom layer: non-woven PP fabric



TECHNICAL DATA

Properties	standard	value	USC units
Mass per unit area	EN 1849-1	1500 g/m ²	4.92 oz/ft ²
Thickness	EN 1849-2	1,3 mm	51 mil
Water vapour transmission (Sd)	EN 1931	120 m	0.029 US Perm
Tensile strength MD/CD	EN 12311-1	500/400 N/50 mm	57/46 lbf/in
Elongation MD/CD	EN 12311-1	40/40 %	-
Resistance to nail tearing MD/CD	EN 12310-1	150/200 N	34/45 lbf
Watertightness (60 kPa)	EN 1928	compliant	-
Resistance to temperature	-	-20/100 °C	-4/212 °F
Reaction to fire	EN 13501-1	class E	-
Resistance to penetration of air	EN 12114	<0,02 m ³ /(m ² h50Pa)	< 0.001 cfm/ft ² at 50Pa
Thermal conductivity (λ)	-	0,2 W/(m·K)	0.12 BTU/h·ft·°F
Specific heat	-	175 J/(kg·K)	-
Density	-	approx. 1300 kg/m ³	approx. 81 lbm/ft ³
Water vapour resistance factor (μ)	EN 13707	approx. 20000	approx. 600 MNs/g
UV stability ⁽¹⁾	EN 13859-1/2	336 h (3 months)	-
After ageing:			
- watertightness (60 kPa)	EN 1296/EN 1928	compliant	-
- tensile strength MD/CD	EN 1297/EN 12311-1	400/300 N/50 mm	46/34 lbf/in
- elongation	EN 1297/EN 12311-1	35/35 %	-
Flexibility at low temperatures	EN 1109	-20 °C	-4 °F
Storage temperature ⁽²⁾	-	+5/+ 40 °C	+41/104 °F

⁽¹⁾Laboratory ageing test data cannot reproduce unforeseeable causes of the product's degradation, or consider the stresses to which it will be subjected during its service life. To ensure its integrity, as a precautionary measure, exposure to weathering during construction should be limited to a maximum of 3 weeks.

⁽²⁾The rolls must be transported and stored in a vertical position. Store the product in a dry, covered location until application, as it is sensitive to temperature fluctuations.

Waste classification (2014/955/EU): 17 03 02.

CODES AND DIMENSIONS

CODE	description	tape	H [m]	L [m]	A [m ²]	H [ft]	L [ft]	A [ft ²]	
BYTUM1500	BYTUM 1500	-	1	25	25	3.3	82	270	30
BYTTTT1500	BYTUM 1500 TT	TT	1	25	25	3.3	82	270	30